

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/00, 4/80	A2	(11) International Publication Number: WO 98/20050 (43) International Publication Date: 14 May 1998 (14.05.98)
(21) International Application Number: PCT/US97/19685 (22) International Filing Date: 29 October 1997 (29.10.97) (30) Priority Data: 60/029,968 1 November 1996 (01.11.96) US (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): PERCEC, Virgil [US/US]; 3482 Roundwood Road, Hunting Valley, OH 44022 (US). (74) Agent: FRICKE, Hilmar, L.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AU, BR, CA, CN, JP, KR, MX, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: POLYMERIZATION OF VINYL MONOMERS (57) Abstract Free radically polymerizable monomers may be polymerized using as an initiator a combination of a selected arylsulfonyl halide or alkylsulfonyl halide and a selected compound containing a lower valent transition metal atom. These polymerizations are sometimes living polymerizations, allowing control of polymer structure such as producing block copolymers and/or polymers with narrow molecular weight distributions. Useful monomers include styrenes and (meth)acrylate esters and amides. The products are useful as molding resins, for glazing, as film forming binders in coating compositions and have numerous other uses.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLE

POLYMERIZATION OF VINYL MONOMERS

FIELD OF THE INVENTION

5 A combination of a selected arylsulfonyl halide or alkylsulfonyl halide and a compound containing a lower valent transition metal atom can be used to initiate free radical polymerizations of vinyl monomers such as (meth)acrylates and styrenes and under certain conditions, these polymerizations may be living.

TECHNICAL BACKGROUND

10 Polymers of so-called vinyl monomers made by free radical polymerization are important items of commerce, for instance poly(methyl methacrylate) is used as a glazing material and molding resin, while polystyrene is useful in packaging as a film, in foam form as in drinking cups, and as a molding resin. Therefore, new polymerization systems for these types of monomers are always of interest, especially
15 when such polymerizations may provide improved or easier control over the microstructure and/or molecular weight of the polymer produced.

V. Percec et al., *Macromolecules*, vol. 28, p. 7970-7972 (1995), V. Percec et al., *Macromolecules*, vol. 29, p. 3665-3668 (1996), B. Barboiu, et al., Abstract of the 36th IUPAC International Symposium on Macromolecules, Aug. 4-9, 1996, Seoul
20 Korea, p. 671, *ibid*, p. 672, V. Percec, et al., Abstract of the 36th IUPAC International Symposium on Macromolecules, p. 68, and V. Percec, et al., *Polym. Prepr.*, vol. 38, No. 1, p. 733-735 (1997), report on the homopolymerization of styrene and other monomers using a combination of an arylsulfonyl chloride and a transition metal compound. Some of these polymerizations are reported to be "living". All of these
25 articles are hereby included by reference.

M. Asscher, et al., *J. Chem. Soc.* (1964) p. 4962-4971 report the reaction of various aryl sulfonyl chlorides or alkyl sulfonyl chlorides and copper chloride with various olefins such as styrene. No polymers are reported to be products.


A. Orochov, et al., *J. Chem. Soc.* (1969) p. 255-259 report on the reaction of
30 cupric chloride with an aryl sulfonyl chloride in the presence of styrene. No polymers are reported.

SUMMARY OF THE INVENTION

This invention concerns a process for the polymerization of vinyl monomers, comprising, contacting a free radically polymerizable vinyl monomer with a first
35 compound of the formula $A^I\text{SO}_2\text{X}$ and a second compound which contains a transition metal atom in a lower valent state, wherein A^I is an aryl, substituted aryl, alkyl or substituted alkyl group, and X is chlorine, bromine or iodine.


DETAILS OF THE INVENTION

Free radically polymerizable vinyl monomers are well known in the art. By a vinyl monomer herein is meant a compound of the formula




- 5 wherein R^1 , R^2 , R^3 and R^4 are hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group, and at least one of R^1 , R^2 , R^3 and R^4 is not hydrogen or alkyl. For a discussion of free radically polymerizable vinyl monomers see for instance H. Mark, et al., Ed., Encyclopedia of Polymer Science and Engineering, 2nd Ed., Vol. 13, John Wiley & Sons, New York, 1988, p. 708-713, which is hereby included by reference.
- 10 Suitable vinyl monomers include various vinyl halides such as vinyl chloride, vinyl fluoride and vinylidene fluoride, selected vinyl ethers such as methyl vinyl ether, chloroprene, isoprene, styrene and substituted styrenes, acrylic esters, methacrylic esters, acrylamides, methacrylamides, and substituted acrylic and methacrylic esters and amides such as 2-chloroethyl methacrylate, 2-methoxyethyl methacrylate, 2-
- 15 hydroxyethyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate, 4-hydroxybutyl (meth)acrylate, 2-aminoethyl (meth)acrylamide and the like.

Preferred vinyl monomers include styrenes and a compound of the formula



- wherein R^5 is hydrogen or methyl and R^6 is $-\text{NR}^7\text{R}^8$ or $-\text{OR}^9$. R^7 and R^8 are each
- 20 independently hydrogen, hydrocarbyl or substituted hydrocarbyl, and R^9 is hydrocarbyl or substituted hydrocarbyl. It is preferred that R^7 and R^8 are each independently hydrogen or alkyl containing 1 to 10 carbon atoms, or R^9 is alkyl containing 1 to 10 carbon atoms, more preferred that R^9 is methyl.

By "a styrene" herein is meant a compound of the formula



- 25 wherein R^{10} is hydrogen or methyl, and R^{11} , R^{12} and R^{13} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group. It is preferred that all of R^{10} , R^{11} , R^{12} and R^{13} are hydrogen.

- In these polymerizations, only one olefin may be present to form a
- 30 homopolymer, or more than one olefin may be present to form a copolymer. If only

one monomer is present it is preferred that it is not styrene. If more than one polymerizable monomer is present at one time a random or alternating copolymer may be formed. Random copolymers are preferred products of the process. Some combinations of monomers may not free radically copolymerize while others will
5 copolymerize. Such combinations are also well known in the art. Also, copolymers of olefins which do not readily homopolymerize under free radical conditions may be prepared using a more readily polymerizable monomer. An example of such monomer a combination is tetrafluoroethylene and ethylene.

By hydrocarbyl herein is meant a group containing carbon and hydrogen. By
10 "substituted" (such as substituted hydrocarbyl or substituted aryl) is meant a group containing an inert substituent group, such as halo, ether, ester, etc. By inert is meant the group does not interfere with the polymerization process described herein. Unless otherwise specified it is preferred that any hydrocarbyl or alkyl groups herein contain 1 to 30 carbon atoms, and any aryl groups contain 6 to 30 carbon atoms. By an aryl
15 group herein is meant a monovalent radical whose free valence is to a carbon atom of an aromatic ring. It is preferred that such rings are carbocyclic. An aryl group may contain a single ring, 2 or more fused rings, or 2 or more aromatic rings connected by covalent bonds. By a functional group herein is meant an inert functional group that does not interfere with the polymerization process described herein. Examples of
20 such groups include alkoxy, aryloxy, ester, amido and halo.

One part of the polymerization system in the present process is an arylsulfonyl halide or an alkyl sulfonyl halide of the formula A^1SO_2X wherein A^1 is an aryl, substituted aryl group, an alkyl group or a substituted alkyl group, and X is chlorine, bromine or iodine. It is preferred that X is chlorine, and/or that A^1 is phenyl,
25 substituted phenyl or methyl. Suitable substituents include one or more of nitro, fluoro, chloro, alkyl, alkoxy, carboxy, hydroxy and dialkylamino. It is more preferred that A^1 is phenyl or p-methoxyphenyl or methyl. Included within the meaning of arylsulfonyl halide or alkylsulfonyl halide is any adduct, such as a 1:1 adduct, which is a reaction product of an aryl or alkyl sulfonyl halide and any polymerizable
30 vinyl monomer. In effect, such an adduct is one of the initial products in the polymerization process itself.

Another component of the polymerization process system is a compound containing a lower valent transition metal atom. By this is meant a compound containing at least one transition metal atom that is capable of existing in a (being
35 oxidized to a) higher valent state. Included within the definition of a compound containing a transition metal atom in a lower valent state is a compound or combination of compounds that under the polymerization process conditions can form in situ the desired compound containing a transition metal atom in a lower valent

state. In some cases this can include metal itself (or an alloy or a metal oxide thereof) which can either be dissolved or slightly dissolve in the process medium. In another instance, CuCl_2 is reported to form CuCl in the presence of styrene [M. Asscher, et al., J. Chem. Soc., (1963), p. 1887], so addition of CuCl_2 to a polymerization in which
5 styrene was present would fulfill the requirement for the presence of a lower valent metal.

Suitable lower valent metals include Cu[I] , Ru[I] , Ni[II] , Fe[II] , Pd[II] , Cu[0] , Ni[0] , Fe[0] , Pd[0] and Rh[II] , and Cu[I] , Ru[I] and Rh(II) are preferred, and Cu[I] is especially preferred. The transition metal compound should preferably be at least
10 slightly soluble in the polymerization medium. Optionally the transition metal compound which is added may be solublized by the addition of certain complexing agents. For example, CuCl may be solublized by the addition of a 2,2'-bipyridine to the process medium, or may be added directly as a 2,2'-bipyridine-type complex. Other useful transition metal compounds are $\text{RhCl[P(C}_6\text{H}_5)_3]_3$ and $\text{RuCl}_2[\text{P(C}_6\text{H}_5)_3]_3$.

15 The molar ratio of lower valent transition metal compound:arylsulfonyl halide or alkyl sulfonyl halide is not critical, but it is preferred that it be greater than 0.2, more preferably greater than 0.5, especially if a living polymerization is desired. It is also preferred that this ratio not be over 5, and more preferably be less than 2.

It is preferred that the polymerization be carried out in a liquid medium, for
20 instance a solvent (for some or all of the starting materials and optionally the polymer) may be added, or the polymerization may be carried out in neat liquid monomer(s) (in bulk). In these bulk polymerizations, conversion to polymer may be limited by increasing viscosity or by formation of "solid" polymer. Useful liquids include aromatic hydrocarbons such as a xylene, and ethers such as 1,4-dioxane and anisole.

25 It is preferred to carry out the polymerization at a temperature of about 0°C to about 200°C , preferably about 50°C to about 175°C and more preferably about 75°C to about 150°C . The upper temperature should not be above the temperature at which significant thermal decomposition of the polymer occurs. Such temperatures are well known for many free radically polymerizable monomers, and are otherwise readily
30 determined.

Since arylsulfonyl halides and alkylsulfonyl halides are hydrolyzed slowly by water, the process can be run under wet conditions. Oxygen may affect free radical polymerizations, so it is also preferred that it be absent. Both of these objectives can be conveniently met by carrying out the polymerization process under an inert
35 atmosphere, such as nitrogen, and starting with dry and deoxygenated ingredients.

The polymerization process described herein may be carried out using methods known to the artisan, see for instance H. Mark, et al., Ed., Encyclopedia of Polymer Science and Engineering, 2nd Ed., Vol. 12, John Wiley & Sons, New York.

1988, p. 504-555. For instance, these polymerizations may be carried out in a batch, semi-batch or continuous manner.

Sometimes the free radical polymerization of olefinic monomers using an aryl or alkyl sulfonyl halide and a lower valent metal compound may possess characteristics of so-called "living" or "controlled" polymerization processes. Such processes can lead to polymers with narrow molecular weight distributions ($M_w/M_n < 2$), as illustrated in Examples 1-6, and may permit formation of block copolymers by sequential addition of polymerizable monomers, see Example 5. For these types of polymerizations, Cu[I], Rh[I], and Ru[II] are preferred low valent metals and Cu[I] is especially preferred, and preferred monomers are styrenes and methacrylic-type compounds, and styrenes are especially preferred. For a discussion of "living" polymerizations see H. Mark, et al., Ed., Encyclopedia of Polymer Science and Engineering, Vol. 8. John Wiley & Sons, New York, 1968, p. 303-325. and H. Mark et. al., Ed., Encyclopedia of Polymer Science and Engineering, 2nd Ed., Supplement Volume, John Wiley & Sons, New York, 1989, p. 429-437, both of which are hereby included by reference.

Often, the polymers produced herein have specific end groups, which are derived from the arylsulfonyl or alkylsulfonyl halide A^1SO_2X , wherein A^1 and X are as defined above. One end group on each polymer chain will be A^1SO_2- and the other end group will be $-X$. This means of course that of the total polymer end groups about half will be A^1SO_2- and the other half will be $-X$. Also the number A^1SO_2- end groups present in the polymer will be approximately equal to number of $-X$ end groups present in the polymer.

In the Examples, the following abbreviations are used:

BA - n-butyl acrylate
BMA - n-butyl methacrylate
GPC - gel permeation chromatography
MMA - methyl methacrylate
Mn - number average molecular weight
Mw - weight average molecular weight
PMMA - poly(methyl methacrylate)
PS - polystyrene
THF - tetrahydrofuran

Example 1

Two ml of styrene (0.0175 mol), 18 mg p-methoxybenzenesulfonyl chloride (8.71×10^{-5} mol), 3 mg of CuCl (3.03×10^{-5} mol) and 25 mg 4,4'-di-n-nonyl-2,2'-bipyridine (6.13×10^{-5} mol) were added to a 25 ml Schlenk tube,

and the solution was degassed by 4 freeze-pump-thaw cycles, and then the tube was filled with argon and heated at 120°C for 17 h. The polymerization was stopped and the viscous solution was analyzed by NMR (conversion to polymer was 67%) and GPC (Mn=15,400, Mw/Mn=1.29, based on a PS standard). Theoretical Mn assuming
5 a living polymerization was 14,000. The polystyrene was isolated by precipitation of a THF solution in methanol, filtration and drying under vacuum.

Example 2

The same procedure is followed as in Example 1, except 1 ml of diphenyl
10 ether is also added to the tube, and polymerization conditions were 120°C for 60 h. The conversion to polymer was 98% (NMR) and the product polystyrene had an Mn of 20,600 and an Mw/Mn of 1.20 by GPC. Theoretical Mn was 20,400. The polystyrene was isolated by the same method as in Example 1.

Example 3

To a 25 ml Schlenk tube were added 3.7 ml MMA (0.035 mol), 18 mg p-methoxybenzenesulfonyl chloride (8.71×10^{-5} mol), 3 mg CuCl (3.03×10^{-5} mol), and 25 mg 4,4'-di-n-nonyl-2,2'-bipyridine (6.13×10^{-5} mol), and the resulting solution was degassed by 4 freeze-pump-thaw cycles, and then the tube was filled with argon and
20 heated at 120°C for 50 h, when conversion was 98% by NMR. PMMA with Mn=40,300 and Mw/Mn=1.23 was obtained. Theoretical Mn was 39,380. The PMMA was isolated by precipitation of a THF solution into methanol, filtering and drying under vacuum.

Example 4

The procedure of Example 3 was followed except that 1 ml of p-xylene was also added to the Schlenk tube, and the polymerization was carried out at 80°C for 150 h, at the end of which time the conversion (by NMR) was 98%. The product PMMA had Mn=40,200, Mw/Mn=1.16. The PMMA was isolated by same method as in
30 Example 3.

Example 5

Example 2 is followed, and at the end of the polymerization reaction of styrene, a 0.1 ml sample is removed and analyzed. Conversion is 98% by NMR, and
35 the polymer has an Mn=20,600 and Mw/Mn=1.20.

Then 3.7 ml of degassed MMA (0.035 mol) are added to the tube and mixed, and then the tube is heated for 6 days at 80°C, at the end of which time 98% (by NMR) of the MMA has been polymerized. The resulting block copolymer has

Mn=60,100, Mw/Mn=1.3, and has a molar ratio of styrene:MMA of 1:2. Eight ml of THF were added to the polymerization mixture, and the polymer was precipitated by addition of this solution to methanol. The block copolymer was filtered and dried under vacuum.

5


Example 6

The procedure of Example 2 was followed, except that 3.7 ml of MMA were also added to the Schlenk tube. Polymerization conditions were 180 h at 120°C. The conversion at that time was 98%. (Note - Conversion can be followed by NMR by removing samples periodically and analyzing them.) The random copolymer had Mn=60,000, Mw/Mn=1.3, and a styrene:MMA ratio of 1:2. Eight ml of THF were added to the polymerization mixture, and the polymer was precipitated by addition of this solution to methanol. The random copolymer was filtered and dried under vacuum.

10
15

Examples 7-12

Neat styrene was mixed with a first compound of the formula



and CuCl/2,2'-bipyridine complex. The molar ratio of the first compound to the CuCl/2,2'-bipyridine complex was 1:1. The polymerization was allowed to proceed at 120°C for the time indicated. Other polymerization conditions and results are given in Table 1. In addition for a polymer made in a similar manner as in Example 12, a 200 MHz ¹H NMR spectrum clearly showed that the end groups for the polymer were p-methoxyphenyl-SO₂- and -Cl. This polymer had Mn=3920 and Mw/Mn=1.49.

20
25

Table 1

Ex. No.	Initial Styrene/CuCl	Y	Time, h	% Conv.	Mn, Found	Mn (Theoretical)	Mw/Mn
7	37.8	NO ₂	72	16.0	1460	850	1.60
8	50.1	H	4.5	72.0	4900	3930	1.63
9	39.4	F	5	88.7	4300	3830	1.80
10	49.1	Cl	4	74.6	3900	4020	1.50
11	51.2	CH ₃	3.5	66.9	3750	3750	1.65
12	50.8	CH ₃ O	2.5	56.1	4000	3170	1.48

Example 13

5 A solution of 6.2 M MMA in xylene, also containing 1-naphthalenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios MMA/1-naphthalenesulfonyl chloride/CuCl/2,2'-bipyridine 200/1/1/3 was made up and held at 90°C. After 4 h, 98% of the MMA was converted to PMMA.

10

Example 14

A solution of 6.2 M MMA in xylene, also containing 2-naphthalenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios MMA/2-naphthalenesulfonyl chloride/CuCl/2,2'-bipyridine 200/1/1/3 was made up and held at 90°C. After 3.3 h, 98% of the MMA was converted to PMMA.

15

Example 15

A solution of 6.2 M MMA in xylene, also containing 5-(N,N-dimethylamino)1-naphthalenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios MMA/5-(N,N-dimethylamino)1-naphthalenesulfonyl
 20 chloride/CuCl/2,2'-bipyridine 200/1/1/3 was made up and held at 90°C. After 6 h, 68% of the MMA was converted to PMMA.

Example 16

A solution of 6.2 M MMA in xylene, also containing
 25 2,5-dichlorobenzenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios MMA/2,5-dichlorobenzenesulfonyl chloride/CuCl/2,2'-bipyridine 200/1/1/3 was made up and held at 90°C. After 5.5 h, 96% of the MMA was converted to PMMA.

Example 17

A solution of 6.2 M MMA in xylene, also containing 2,5-dimethoxybenzenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios MMA/2,5-dimethoxybenzenesulfonyl chloride/CuCl/2,2'-bipyridine 200/1/1/3 was
5 made up and held at 90°C. After 3.8 h, 90% of the MMA was converted to PMMA.

Example 18

A solution of 4.9 M BMA in phenyl ether, also containing 4-carboxybenzenesulfonyl chloride, CuCl and 2,2'-bipyridine in the molar ratios
10 MMA/4-carboxybenzenesulfonyl chloride/CuCl/2,2'-bipyridine 200/1/1/3 was made up and held at 120°C. After 8 h, 83% of the BMA was converted to polymer.

Example 19

A solution of 3.16 M BA in phenyl ether, also containing
15 4-methoxybenzenesulfonyl chloride, CuCl and 4,4'-dinonyl-2,2'-bipyridine in the molar ratios MMA/4-methoxybenzenesulfonyl chloride/CuCl/4,4'-dinonyl-2,2'-bipyridine 200/1/0.3/0.42 was made up and held at 140°C. After 48 h, 60% of the BA was converted to polymer.

Example 20

A solution of 6.25 M MMA in p-xylene, also containing 4-methoxybenzenesulfonyl chloride, CuCl and 4,4'-dinonyl-2,2'-bipyridine in the molar ratios MMA/4-methoxybenzenesulfonyl
20 chloride/CuCl/4,4'-dinonyl-2,2'-bipyridine 100/1/0.3/0.42 was made up and held at 80°C. After 20 h, 40% of the MMA was converted to PMMA.

Example 21

BMA (3g, 21.1 mmol), phenyl ether, (1.4 M), methyl sulfonyl chloride (12 mg, 0.105 mmol), CuCl (10 mg, 0.105 mmol) and 2,2' bipyridine (49 mg, 0.315
30 mmol) were weighted directly in a 25 ml Schlenk tube. The mixture was degassed by four freeze-pump-thaw cycles, filled with Ar and heated at 120°C for 1 hour. A sample was diluted with CDCl₃ in NMR tube and the conversion was determined by ¹H-NMR spectroscopy to be 95%. Then, part of the solution was filtered and injected in a GPC column eluted with THF (tetrahydrofuran) and the molecular weight was
35 measured versus PMMA standards using a RI detector. The polymer has $M_n = 24,000$, $M_{th} = 25,000$ and $M_w/M_n = 1.27$.

Example 22

BMA (3g, 21.1 mmol), phenyl ether (1.4M), 4-methoxy benzeone sulfonyl chloride, (21.6 mg, 0.104 mmol), cuprous oxide (15 mg, 0.104 mmol) and 2,2'bipyridine (33 mg, 0.211 mmol) were weighted directly in a 25 ml Schlenk tube.

5 The mixture was degassed by four freeze-pump-thaw cycles, filled with Ar and heated at 120°C for 5 hours. A sample was diluted with CDCl₃ in NMR tube and the conversion was determined by ¹H-NMR spectroscopy to be 90%. Then, part of the solution was filtered and injected in a GPC column eluted with THF and the molecular weight was measured versus PS standards using a UV detector. The

10 polymer has $M_n = 22,000$, $M_{th} = 25,000$ and $M_w/M_n = 1.14$.

Example 23

BMA (3 g, 21.1 mmol) phenyl ether (1.4M), 4-methoxy benzene sulfonyl chloride, (21.6 mg, 0.104 mmol), Cu metal powder (a Cu wire or film can also be


15 used), [3.4 mg, 0.053 mmol] and 2,2' bipyridine (16 mg, 0.11 mmol) were weighted directly in a 25 ml Schlenk tube. The mixture was degassed by four freeze-pump-thaw cycles, filled with Ar and heated to 120°C for 2 hours. A sample was diluted with CDCl₃ in NMR tube and the conversion was determined by ¹H-NMR spectroscopy to be 97%. Then, part of the solution was filtered and injected in a GPC

20 column eluted with THF and the molecular weight was measured versus PS standards using a UV detector. The polymer has $M_n = 27,000$, $M_{th} = 27,600$ and $M_w/M_n = 1.24$.

CLAIMS

What is claimed is:

1. A process for the polymerization of vinyl monomers, comprising, contacting a free radically polymerizable vinyl monomer with a first compound of the formula A^1SO_2X and a second compound which contains a transition metal atom in a lower valent state, wherein A^1 is an aryl, substituted aryl, alkyl or substituted alkyl group, and X is chlorine, bromine or iodine.
2. The process as recited in claim 1 wherein said transition metal atom is Cu[I], Ru[I], Ni[II], Fe[II], Pd[II] or Rh[II].
3. The process as recited in claim 1 wherein said transition metal atom is and Cu[I], Ru[I] or Rh(II).
4. The process as recited in claim 1 wherein said transition metal atom is Cu[I].
5. The process as recited in claim 1 wherein said transition metal compound is a CuCl-2,2'-bipyridine-type complex.
6. The process as recited in claim 1 wherein said monomer is a styrene or a compound of the formula



- wherein R^5 is hydrogen or methyl and R^6 is $-NR^7R^8$ or $-OR^9$, R^7 and R^8 are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl, and R^9 is hydrocarbyl or substituted hydrocarbyl.
7. The process as recited in claim 6 wherein said monomer is styrene, or R^7 and R^8 are each independently hydrogen or alkyl containing 1 to 10 carbon atoms or R^9 is alkyl containing 1 to 10 carbon atoms.
 8. The process as recited in claim 1 wherein Ar^1 is phenyl or substituted phenyl and X is chlorine.
 9. The process as recited in claim 1 wherein X is chlorine.
 10. The process as recited in claim 1 carried out at a temperature of about 0°C to about 200°C .
 11. The process as recited in claim 1 carried out at a temperature of about 75°C to about 150°C .
 12. The process as recited in claim 3 wherein a polymer produced has $M_w/M_n < 2$, and a ratio of said first compound:said second compound is greater than about 0.2.

13. The process as recited in claim 3 wherein a block copolymer is produced by sequential addition of monomers, and a ratio of said first compound:said second compound is greater than about 0.2.

14. The process as recited in claim 1 wherein a homopolymer is produced.

5 15. The process as recited in claim 14 wherein said homopolymer is not polystyrene.

16. The process as recited in claim 1 wherein a random or alternating copolymer is produced.

10 17. The process as recited in claim 1 wherein a ratio of said first compound:said second compound is greater than about 0.2.

18. The process as recited in claim 1 wherein a ratio of said first compound:said second compound is greater than about 0.5, and less than about 5.

19. The process as recited in claim 1 wherein a random copolymer is produced.

15